






TSF-5000

1990's Legacy filter inductor material

Initial Permeability 5000+/- 25%

Curie Temperature > 170 Celsius

Saturation Flux Density @ 15 Oersteds 4300 gauss



TSC FERRITE International 847-249-4900 or Fax 847-249-4988